

# Material: ASTM B 162 N02200

## Standard Specification for Nickel Plate, Sheet and Strip

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** ASTM B 162 N02200 Nickel Plate, Sheet and Strip

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	0.350 max.
Manganese	Mn %	0.350 max.
Copper	Cu %	0.250 max.
Sulphur	S %	0.010 max.
Iron	Fe %	0.400 max.
Nickel	Ni %	99.000 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	380 min.
Yield Strength in Mpa	100 min.
Elongation in %	2 min.
Reduction of Area in %	-
Hardness in HRC	64 - 91
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 160 N02200	ASTM	USA	Rod and Bar
B 161 N02200	ASTM	USA	Pipe and Tube
B 163 N02200	ASTM	USA	Tube
B 564 N02200	ASTM	USA	Forging
B 725 N02200	ASTM	USA	Pipe
N02200	UNS	USA	Pipe
NNCP	JIS	Japan	Sheet and Plate

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India