

Material: ASTM B 21 C48500

Standard Specification for Naval Brass Rod, Bar and Shapes

Group: Non Ferrous Copper Alloys

Sub Group: ASTM B 21 C48500 Naval Brass Rod, Bar and Shapes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Lead	Pb %	1.300 - 2.200		
Tin	Sn %	0.500 - 1.000		
Copper	Cu %	59.000 - 62.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	345 min.
-	-	-	Yield Strength in Mpa	140 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	60 - 90
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn36Pb2Sn1	DIN	Germany	Rod
B 124 C48500	ASTM	USA	Rod, Bar and Shape
B 283 C48500	ASTM	USA	Forging
SB-283 C48500	ASME	USA	Forging
2.0371	DIN	Germany	Rod
485	AS	Australia	Forging
C48500	AS	Australia	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com