

## Material: ASTM B 26 712.0

### Standard Specification for Aluminium Alloy Sand Casting

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** ASTM B 26 Aluminium Alloy Sand Casting

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.250 max.	As-Cast	
Iron	Fe %	0.500 max.		
Magnesium	Mg %	0.500 - 0.650		
Manganese	Mn %	0.100 max.		
Silicon	Si %	0.300 max.		
Titanium	Ti %	0.150 - 0.250		
Zinc	Zn %	5.000 - 6.500		
Chromium	Cr %	0.400 - 0.600		
Other	Ot%	0.200 max.		
Aluminium	Al %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa 235 min. Yield Strength in Mpa 170 min. Elongation in % 4 min. Reduction of Area in % - Hardness in HB 75 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM31	BS	British	Ingot and Casting
712.0	AA	USA	Casting
Al Zn5Mg	ISO	International	Ingot and Casting
712.0	SAE	USA	Casting
BA701	AS	Australia	Ingot and Casting
L-2710	UNE	Spain	Ingot and Casting
A-Z5G	AFNOR NF	France	Ingot and Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)