

Material: ASTM B 333 N10629

Standard Specification for Nickel-Molybdenum Alloy Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 333 N10629 Nickel-Molybdenum Alloy Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.050 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	0.500 - 1.500		
Iron	Fe %	1.000 - 6.000		
Molybdenum	Mo %	26.000 - 30.000	Mechanical Properties	
Aluminium	Al %	0.100 - 0.500	Tensile Strength in Mpa	760 min.
Copper	Cu %	0.500 max.	Yield Strength in Mpa	350 min.
Nickel	Ni %	Balance	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	100 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 335 N10629	ASTM	USA	Rod
B 564 N10629	ASTM	USA	Forging
B 472 N10629	ASTM	USA	Bar
B 619 N10629	ASTM	USA	Pipe
B 622 N10629	ASTM	USA	Pipe and Tube
B 626 N10629	ASTM	USA	Tube
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com