

Material: ASTM B 335 N10001

Standard Specification for Nickel-Molybdenum Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 335 N10001 Nickel-Molybdenum Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	1.000 max.		
Iron	Fe %	4.000 - 6.000		
Molybdenum	Mo %	26.000 - 30.000	Mechanical Properties	
Vanadium	V %	0.200 - 0.400	Tensile Strength in Mpa	690 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	315 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 333 N10001	ASTM	USA	Plate, Sheet and Strip
B 619 N10001	ASTM	USA	Pipe
B 622 N10001	ASTM	USA	Pipe and Tube
B 626 N10001	ASTM	USA	Tube
SB-333 N1001	ASME	USA	Plate, Sheet and Strip
N10001	UNS	USA	Plate, Sheet and Strip
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com