

## Material: ASTM B 344 Ni60-Cr16

### Standard Specification for Drawn or Rolled Nickel-Chromium and Nickel-Chromium-Iron Alloys for Electrical Heating Elements

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** ASTM B 344 Ni60-Cr16 Drawn or Rolled Nickel-Chromium and Nickel-Chromium-Iron Alloys for Electrical Heating Elements

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Wire & Strip with Hot & Cold Rolled

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.750 - 1.750		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 18.000		
Sulphur	S %	0.010 max.		
Nickel	Ni %	57.000 min.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % 10 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)