

Material: ASTM B 408 N08811

Standard Specification for Nickel-Iron-Chromium Alloy Rod and Bar

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 408 N08811 Nickel-Iron-Chromium Alloy Rod and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.100	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	19.000 - 23.000		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Aluminium	Al %	0.150 - 0.600		
Sulphur	S %	0.015 max.		
Copper	Cu %	0.750 max.		
Titanium	Ti %	0.250 - 0.600		
Iron	Fe %	39.500 max.		
Phosphorus	P %	0.045 max.	Mechanical Properties	
Nickel	Ni %	30.000 - 35.000	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N08811	ASTM	USA	Tube
B 407 N08811	ASTM	USA	Pipe and Tube
B 409 N08811	ASTM	USA	Plate, Sheet and Strip
B 564 N08811	ASTM	USA	Forging
SB-163 N08811	ASME	USA	Tube
N08811	UNS	USA	Tube
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com