

Material: ASTM B 409 N08120

Standard Specification for Nickel-Iron-Chromium Alloy Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 409 N08120 Nickel-Iron-Chromium Alloy Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Chemical Composition		
Carbon	C %	0.020 - 0.100	Nickel	Ni %	35.000 -
Silicon	Si %	1.000 max.	Iron	Fe %	Balance
Manganese	Mn %	1.500 max.	-	-	-
Chromium	Cr %	23.000 - 27.000	-	-	-
Sulphur	S %	0.030 max.	-	-	-
Boron	B %	0.010 max.	Heat Treatment		
Copper	Cu %	0.500 max.	As-Cast or Annealing or Age Hardning		
Aluminium	Al %	0.400 max.	Mechanical Properties		
Titanium	Ti %	0.200 max.	Tensile Strength in Mpa	621 min.	
Niobium	Nb %	0.400 - 0.900	Yield Strength in Mpa	276 min.	
Molybdenum	Mo %	2.500 max.	Elongation in %	30 min.	
Phosphorus	P %	0.040 max.	Reduction of Area in %	-	
Tungsten	W %	2.500 max.	Hardness in BHN	-	
Cobalt	Co %	3.000 max.	Impact in Joule	-	
Nitrogen	N %	0.150 - 0.300			

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N08120	ASTM	USA	Tube
B 407 N08120	ASTM	USA	Pipe and Tube
B 408 N08120	ASTM	USA	Rod and Bar
B 564 N08120	ASTM	USA	Forging
SB-163 N08120	ASME	USA	Tube
N08120	UNS	USA	Forging
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com