

Material: ASTM B 409 N08890

Standard Specification for Nickel-Iron-Chromium Alloy Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 409 N08890 Nickel-Iron-Chromium Alloy Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.140	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 - 2.000		
Manganese	Mn %	1.500 max.		
Chromium	Cr %	23.500 - 28.500		
Copper	Cu %	0.750 max.		
Sulphur	S %	0.015 max.		
Aluminium	Al %	0.050 - 0.600		
Titanium	Ti %	0.150 - 0.600		
Molybdenum	Mo %	1.000 - 2.000		
Niobium	Nb %	0.200 - 1.000		
			Mechanical Properties	
Tantalum	Ta %	0.100 - 0.600	Tensile Strength in Mpa	520 min.
Nickel	Ni %	40.000 - 45.000	Yield Strength in Mpa	205 min.
Iron	Fe %	Balance	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 408 N08890	ASTM	USA	Rod and Bar
B 407 N08890	ASTM	USA	Pipe and Tube
SB-407 N08890	ASME	USA	Pipe and Tube
SB-408 N08890	ASME	USA	Rod and Bar
SB-409 N08890	ASME	USA	Plate, Sheet and Strip
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com