

Material: ASTM B 446 N06625

Standard Specification for Nickel-Chromium-Molybdenum-Columbium Alloy, Rod and Bar

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 446 N06625 Nickel-Chromium-Molybdenum-Columbium Alloy, Rod and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	20.000 - 23.000		
Sulphur	S %	0.015 max.		
Phosphorus	P %	0.0150 max.		
Nb + Ta	Nb% + Ta%	3.150 - 4.150		
Cobalt	Co %	1.000 max.		
Molybdenum	Mo %	8.000 - 10.000		
Iron	Fe %	5.000 max.		
			Mechanical Properties	
Aluminium	Al %	0.400 max.	Tensile Strength in Mpa	690 min.
Titanium	Ti %	0.400 max.	Yield Strength in Mpa	276 min.
Nickel	Ni %	58.000 min.	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 443 N06625 Grade 1	ASTM	USA	Plate, Sheet and Strip
B 443 N06625 Grade 2	ASTM	USA	Plate, Sheet and Strip
B 444 N06625 Grade 1	ASTM	USA	Pipe and Tube
B 444 N06625 Grade 2	ASTM	USA	Pipe and Tube
B 704 N06625	ASTM	USA	Tube
B 705 N06625 Grade 1	ASTM	USA	Pipe
B 705 N06625 Grade 2	ASTM	USA	Pipe

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com