

Material: ASTM B 464 N08024

Standard Specification for Nickel Alloy Pipe

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 464 N08024 Nickel Alloy Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 - 1.500		
Sulphur	S %	0.035 max.		
Chromium	Cr %	22.500 - 25.000		
Phosphorus	P %	0.035 max.		
Molybdenum	Mo %	3.500 - 5.000		
Nb + Ta	Nb% + Ta%	0.150 - 0.350	Mechanical Properties	
Nickel	Ni %	35.000 - 40.000	Tensile Strength in Mpa	551 min.
Iron	Fe %	Balance	Yield Strength in Mpa	241 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 463 N08024	ASTM	USA	Plate, Sheet and Strip
SB-462 N08024	ASME	USA	Pipe Flange, Forged Fitting and Valve
B 472 N08024	ASTM	USA	Billets and Bars for Reforging
B 473 N08024	ASTM	USA	Bar and Wire
B 475 N08024	ASTM	USA	Wire
B 729 N08024	ASTM	USA	Pipe and Tube
SB-464 N08024	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India