

Material: ASTM B 472 N08020

Standard Specification for Nickel Alloy Billets and Bars for Reforging

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 472 N08020 Nickel Alloy Billets and Bars for Reforging

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Billets and Bars for Reforging

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Copper	Cu %	3.000 - 4.000		
Sulphur	S %	0.035 max.		
Chromium	Cr %	19.000 - 21.000		
Phosphorus	P %	0.045 max.		
Molybdenum	Mo %	2.000 - 3.000		
Nb + Ta	Nb% + Ta%	1.000 max.	Mechanical Properties	
Nickel	Ni %	32.000 - 38.000	Tensile Strength in Mpa	551 min.
Iron	Fe %	Balance	Yield Strength in Mpa	241 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 462 N08020	ASTM	USA	Pipe Flange, Forged Fitting and Valve
B 463 N08020	ASTM	USA	Plate, Sheet and Strip
B 464 N08020	ASTM	USA	Pipe
B 468 N08020	ASTM	USA	Tube
B 473 N08020	ASTM	USA	Bar and Wire
B 475 N08020	ASTM	USA	Wire
B 729 N08020	ASTM	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com