

Material: ASTM B 472 N08926

Standard Specification for Nickel Alloy Billets and Bars for Reforging

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 472 N08926 Nickel Alloy Billets and Bars for Reforging

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Billet and Bar

Chemical Composition		
Carbon	C %	0.020 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	2.000 max.
Chromium	Cr %	19.000 - 21.000
Sulphur	S %	0.010 max.
Molybdenum	Mo %	6.000 - 7.000
Phosphorus	P %	0.030 max.
Copper	Cu %	0.500 - 1.500
Nitrogen	N %	0.150 - 0.250
Nickel	Ni %	24.000 - 26.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast or Annealing or Age Hardening	

Mechanical Properties	
Tensile Strength in Mpa	650 min.
Yield Strength in Mpa	295 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 649 N08926	ASTM	USA	Bar and Wire
A 182 F1925N	ASTM	USA	Pipe Flanges, Forged Fittings and Valves
B 625 N08926	ASTM	USA	Plate, Sheet and Strip
B 673 N08926	ASTM	USA	Pipe
B 674 N08926	ASTM	USA	Tube
B 677 N08926	ASTM	USA	Pipe and Tube
SB-625 N08926	ASME	USA	Plate, Sheet and Strip

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India