

Material: ASTM B 472 N12160

Standard Specification for Nickel Alloy Billets and Bars for Reforging

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 472 N12160 Nickel Alloy Billets and Bars for Reforging

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Billet and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	2.400 - 3.000		
Manganese	Mn %	1.500 max.		
Chromium	Cr %	26.000 - 30.000		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	1.000 max.		
Phosphorus	P %	0.030 max.		
Titanium	Ti %	0.020 - 0.800		
Iron	Fe %	3.500 max.		
Tungsten	W %	1.000 max.	Mechanical Properties	
Cobalt	Co %	27.000 - 33.000	Tensile Strength in Mpa	620 min.
Niobium	Nb %	1.000 max.	Yield Strength in Mpa	240 min.
Nickel	Ni %	Balance	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N1216	ASTM	USA	Forging
B 619 N12160	ASTM	USA	Pipe
B 622 N12160	ASTM	USA	Pipe and Tube
B 626 N12160	ASTM	USA	Tube
B 435 N12160	ASTM	USA	Plate, Sheet and Strip
B 572 N12160	ASTM	USA	Rod
SB-564 N12160	ASME	USA	Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com