

Material: ASTM B 512 N08330

Standard Specification for Nickel-Chromium-Silicon Alloy Billets and Bars

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 512 N08330 Nickel-Chromium-Silicon Alloy Billets and Bars

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Billets and Bar

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	0.750 - 1.500
Manganese	Mn %	2.000 max.
Chromium	Cr %	17.000 - 20.000
Sulphur	S %	0.030 max.
Copper	Cu %	1.000 max.
Phosphorus	P %	0.030 max.
Nickel	Ni %	34.000 - 37.000
Lead	Pb %	0.005 max.
Tin	Sn %	0.025 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	210 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 511 N08330	ASTM	USA	Bar and Shape
B 535 N08330	ASTM	USA	Pipe and Tube
B 536 N08330	ASTM	USA	Plate, Sheet and Strip
B 710 N08330	ASTM	USA	Pipe
B 739 N08330	ASTM	USA	Tube
SB-511 N08330	ASME	USA	Bar and Shape
SB-535 N08330	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India