

Material: ASTM B 572 R30556

Standard Specification for Nickel-Iron-Chromium-Molybdenum Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 572 R30556 Nickel-Iron-Chromium-Molybdenum Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition		
Carbon	C %	0.050 - 0.150
Silicon	Si %	0.200 - 0.800
Manganese	Mn %	0.500 - 2.000
Chromium	Cr %	21.000 - 23.000
Sulphur	S %	0.015 max.
Molybdenum	Mo %	2.500 - 4.000
Phosphorus	P %	0.040 max.
Cobalt	Co %	16.000 - 21.000
Aluminium	Al %	0.100 - 0.500
Lanthanum	La %	0.005 - 0.100
Boron	B %	0.020 max.
Niobium	Nb %	0.030 max.
Tantalum	Ta %	0.300 - 1.250
Nitrogen	N %	0.100 - 0.300
Tungsten	W %	2.000 - 3.500

Chemical Composition		
Zirconium	Zr %	0.001 - 0.100
Nickel	Ni %	19.000 -
Iron	Fe %	Balance
-	-	-
-	-	-
Heat Treatment		
As-Cast or Annealing or Age Hardning		
Mechanical Properties		
Tensile Strength in Mpa	690 min.	
Yield Strength in Mpa	310 min.	
Elongation in %	40 min.	
Reduction of Area in %	-	
Hardness in BHN	-	
Impact in Joule	-	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 619 R30556	ASTM	USA	Pipe
B 622 R30556	ASTM	USA	Pipe
B 626 R30556	ASTM	USA	Tube
B 435 R30566	ASTM	USA	Plate, Sheet and Strip
B 472 R30566	ASTM	USA	Billets and Bars for Reforging
SB-619 R30556	ASME	USA	Pipe
SB-622 R30556	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com