

Material: ASTM B 574 N06058

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 574 N06058 Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	20.000 - 23.000		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	18.500 - 21.000		
Phosphorus	P %	0.015 max.		
Cobalt	Co %	0.300 max.		
Iron	Fe %	1.500 max.		
Aluminium	Al %	0.400 max.		
Copper	Cu %	0.500 max.	Mechanical Properties	
Tungsten	W %	0.300 max.	Tensile Strength in Mpa	760 min.
Nitrogen	N %	0.020 - 0.150	Yield Strength in Mpa	360 min.
Nickel	Ni %	Balance	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06058	ASTM	USA	Forging
B 575 N06058	ASTM	USA	Plate, Sheet and Strip
B 619 N06058	ASTM	USA	Pipe
B 622 N06058	ASTM	USA	Pipe and Tube
B 626 N06058	ASTM	USA	Tube
SB-564 N06058	ASME	USA	Forging
SB-574 N06058	ASME	USA	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India