

## Material: ASTM B 582 N06030

### Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Plate, Sheet and Strip

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** ASTM B 582 N06030 Nickel-Chromium-Iron-Molybdenum-Copper Alloy Plate, Sheet and Strip

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.500 max.		
Chromium	Cr %	28.000 - 31.500		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	5.000 max.		
Copper	Cu %	1.000 - 2.400	Mechanical Properties	
Tungsten	W %	1.500 - 4.000	Tensile Strength in Mpa	586 min.
Nb + Ta	Nb% + Ta%	0.300 - 1.500	Yield Strength in Mpa	241 min.
Iron	Fe %	13.000 - 17.000	Elongation in %	30 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06030	ASTM	USA	Rod
B 462 N06030	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 N06030	ASTM	USA	Pipe
B 622 N06030	ASTM	USA	Pipe and Tube
B 626 N06030	ASTM	USA	Tube
B 472 N06030	ASTM	USA	Billets and Bars
SB-581 N06030	ASME	USA	Rod

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)