

Material: ASTM B 622 N06255

Standard Specification for Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 622 N06255 Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	23.000 - 26.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 9.000		
Phosphorus	P %	0.030 max.		
Copper	Cu %	1.200 max		
Titanium	Ti %	0.690 max.		
Tungsten	W %	3.000 max.		
			Mechanical Properties	
Nickel	Ni %	47.000 - 52.000	Tensile Strength in Mpa	586 min.
Iron	Fe %	Balance	Yield Strength in Mpa	221 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N06255	UNS	USA	Pipe and Tube
SB-622 N06255	ASME	USA	Pipe and Tube
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com