

Material: ASTM B 626 N06030

Standard Specification for Nickel and Nickel-Cobalt Alloy Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 626 N06030 Nickel and Nickel-Cobalt Alloy Tube

Application : Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.500 max.		
Chromium	Cr %	28.000 - 31.500		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Nb + Ta	Nb% + Ta%	0.300 - 1.500	Mechanical Properties Tensile Strength in Mpa 586 min. Yield Strength in Mpa 241 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Tungsten	W %	1.500 - 4.000		
Copper	Cu %	1.000 - 2.400		
Cobalt	Co %	5.000 max.		
Iron	Fe %	13.000 - 17.000		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06030	ASTM	USA	Rod
B 582 N06030	ASTM	USA	Plate, Sheet and Strip
B 462 N06030	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 N06030	ASTM	USA	Pipe
B 622 N06030	ASTM	USA	Pipe and Tube
B 472 N06030	ASTM	USA	Billets and Bars
SB-581 N06030	ASME	USA	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com