

Material: ASTM B 626 N06230

Standard Specification for Nickel and Nickel-Cobalt Alloy Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 626 N06230 Nickel and Nickel-Cobalt Alloy Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.250 - 0.750		
Manganese	Mn %	0.300 - 1.000		
Chromium	Cr %	20.000 - 24.000		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	1.000 - 3.000		
Phosphorus	P %	0.030 max.		
Boron	B %	0.015 max.		
Lanthanum	La %	0.005 - 0.050		
Iron	Fe %	3.000 max.	Mechanical Properties	
Aluminium	Al %	0.500 max.	Tensile Strength in Mpa	760 min.
Tungsten	W %	13.000 - 15.000	Yield Strength in Mpa	310 min.
Cobalt	Co %	5.000 max.	Elongation in %	40 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 619 N06230	ASTM	USA	Pipe
B 622 N06230	ASTM	USA	Pipe and Tube
B 435 N06230	ASTM	USA	Sheet, Strip and Plate
B 472 N06230	ASTM	USA	Billets and Bars for Reforging
SB-435 N06230	ASME	USA	Plate, Sheet and Strip
SB-564 N06230	ASME	USA	Forging
SB-572 N06230	ASME	USA	Sheet, Strip and Plate

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com