

Material: ASTM B 775 N06600

Standard Specification for Nickel-Chromium-Iron-Alloy Pipe

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 775 N06600 Nickel-Chromium-Iron-Alloy Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	14.000 - 17.000		
Iron	Fe %	6.000 - 10.000		
Nickel	Ni %	72.000 min.		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	655 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06600	ASTM	USA	Forging
B 366 N06600	ASTM	USA	Forging
B 516 N06600	ASTM	USA	Tube
B 517 N06600	ASTM	USA	Pipe
B 564 N06600	ASTM	USA	Forging
B 751 N06600	ASTM	USA	Pipe
B 829 N06600	ASTM	USA	Pipe

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com