

Material: ASTM B1007 N07725 Type 3

Standard Specification for Precipitation Hardenable or Cold Worked, Nickel Alloy Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B1007 N07725 Type 3 Precipitation Hardenable or Cold Worked, Nickel Alloy Tube

Application : Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	0.200 max.		
Manganese	Mn %	0.350 max.		
Chromium	Cr %	19.000 - 22.500		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	7.000 - 9.500		
Phosphorus	P %	0.015 max.		
Niobium	Nb %	2.750 - 4.000		
Titanium	Ti %	1.000 - 1.700		
			Mechanical Properties	
Aluminium	Al %	0.350 max.	Tensile Strength in Mpa	724 min.
Nickel	Ni %	55.000 - 59.000	Yield Strength in Mpa	276 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	20 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 805 N07725	ASTM	USA	Bar and Wire
B 872 N07725	ASTM	USA	Plate, Sheet and Strip
B 983 N07725 Type 1	ASTM	USA	Pipe and Tube
B 983 N07725 Type 2	ASTM	USA	Pipe and Tube
B1007 N07725 Type 1	ASTM	USA	Tube
B1007 N07725 Type 2	ASTM	USA	Tube
N07725	UNS	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com