

## Material: ASTM B122 C77000

### Standard Specification for Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Alloy Plate, Sheet, Strip and Rolled Bar

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASTM B122/B122M Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Alloy Plate, Sheet, Strip and Rolled Bar

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Plate, Sheet, Strip and Rolled Bar

Chemical Composition			Heat Treatment	
Iron	Fe %	0.250 max.	Normalizing or Annealing or Tempering	
Manganese	Mn %	0.500 max.		
Ni + Co	Ni% + Co%	16.500 - 19.500		
Lead	Pb %	0.050 max.		
Copper	Cu %	53.500 - 56.500		
Zinc	Zn %	Balance		
-	-	-		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      415 - 850 Yield Strength in Mpa      29 - 100 Elongation in %      - Reduction of Area in %      - Hardness in BHN      - Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi18Zn27	IS	India	Rod and Bar
CuNi18Zn27	ISO	International	Plate, Sheet and Strip
B151 C77000	ASTM	USA	Rod and Bar
B206 C77000	ASTM	USA	Wire
CuNi18Zn20	ISO	International	Plate, Sheet and Strip
CuNi18Zn27	AFNOR NF	France	Plate, Sheet and Strip
CuNi18Zn27	DIN	Germany	Plate, Sheet and Strip

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)