

# Material: ASTM B124 UNS C65500

## Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASTM B124 Copper and Copper Alloy Forging Rod, Bar and Shapes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Rod, Bar and Shape

Chemical Composition		
Lead	Pb %	0.050 max.
Iron	Fe %	0.800 max.
Ni + Cu	Ni% + Cu%	0.600 max.
Silicon	Si %	2.800 - 3.800
Manganese	Mn %	0.500 - 1.300
Zinc	Zn %	1.500 max.
Copper	Cu %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Annealing or Tempering

Mechanical Properties	
Tensile Strength in Mpa	344 min.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C65500	AS	Australia	Ingot and Casting
B100 C65500	ASTM	USA	Plate and Sheet
B283 C65500	ASTM	USA	Forging
B96 C65500	ASTM	USA	Plate, Sheet, Strip and Bar
B98 C65500	ASTM	USA	Rod, Bar and Shape
SB-98 C65500	ASME	USA	Rod, Bar and Shape
SB-283 C65500	ASME	USA	Forging

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 **Email:** [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India