

Material: ASTM B147-8A

Standard Specification for Copper Alloy Sand Casting for General Applications

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B147 Copper Alloy Sand Casting for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.500 - 1.500	As-Cast	
Iron	Fe %	0.400 - 2.000		
Manganese	Mn %	0.100 - 1.500		
Ni + Co	Ni% + Co%	1.000 max.		
Lead	Pb %	0.400 max.		
Tin	Sn %	1.000 max.		
Zinc	Zn %	36.000 - 42.000		
Copper	Cu %	55.000 - 60.000		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	448 min.
			Yield Strength in Mpa	172 min.
			Elongation in %	20 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C86500	UNS	USA	Rod, Bar, Tube and Shapes
SB-505 C86500	ASME	USA	Casting
SB-584 C86500	SAE	USA	Casting
C86500	SAE	USA	Casting
CA865	SAE	USA	Casting
SAE 43	SAE	USA	Casting
C86500	AS	Australia	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com