

Material: ASTM B224 C14700

Standard Specification for Copper and Copper-Alloy

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B224 Copper and Copper-Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.002 - 0.005	Normalizing or Annealing or Tempering	
Sulphur	S %	0.200 - 0.500		
Copper	Cu %	99.90 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	154.500 - 698.200
-	-	-	Yield Strength in Mpa	55 - 367
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C14700	UNS	USA	Rod, Bar, Tube and Shapes
B283 C14700	ASTM	USA	Forging
B301 C14700	ASTM	USA	Rod, Bar, Wire and Shapes
SB-283 C14700	ASME	USA	Forging
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com