

Material: ASTM B271 C85400

Standard Specification for Copper-Base Alloy Centrifugal Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B271 Copper-Base Alloy Centrifugal Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.350 max.	As-Cast	
Iron	Fe %	0.700 max.		
Ni + Co	Ni% + Co%	1.000 max.		
Lead	Pb %	1.500 - 3.800		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.500 - 1.500		
Zinc	Zn %	24.000 - 32.000		
Copper	Cu %	65.000 - 70.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	207 min.
-	-	-	Yield Strength in Mpa	76 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C85400	UNS	USA	Rod, Bar, Tube and Shapes
B30 C85400	ASTM	USA	Ingots and Casting
B584 C85400	ASTM	USA	Casting
C85400	SAE	USA	Casting
CA854	SAE	USA	Casting
C85400	AS	Australia	Casting
CACIn202	KS	Korea	Ingots and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com