

Material: ASTM B271 High-Lead Tin Bronze UNS C93800

Standard Specification for Copper-Base Alloy Centrifugal Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B271 Copper-Base Alloy Centrifugal Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	6.300 - 7.500	As-Cast	
Lead	Pb %	13.000 - 16.000		
Zinc	Zn %	0.800 max.		
Iron	Fe %	0.150 max.		
Ni + Co	Ni% + Co%	1.000 max.		
Aluminium	Al %	0.005 max.		
Silicon	Si %	0.005 max.		
Antimony	Sb %	0.800 max.		
Sulphur	S %	0.080 max.		
Phosphorus	P %	0.050 max.		
Copper	Cu %	75.000 - 79.000	Mechanical Properties Tensile Strength in Mpa 207 min. Yield Strength in Mpa 83 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C93800	ASTM	USA	Ingots and Castings
B66 C93800	ASTM	USA	Ingots and Castings
SB-505 C93800	ASME	USA	Casting
SB-584 C93800	ASME	USA	Casting
C93800	SAE	USA	Casting
CA938	SAE	USA	Casting
CACIn604	KS	Korea	Ingots and Castings

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com