

Material: ASTM B275 384.0

Standard Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

Group: Non-Ferrous Aluminium Alloy

Sub Group: ASTM B275 Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	3.000 - 4.500	As-Cast	
Iron	Fe %	1.300 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.500 max.		
Silicon	Si %	10.500 - 12.000		
Tin	Sn %	0.350 max.		
Zinc	Zn %	3.000 max.		
Other	Ot%	0.500 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 330 min. Yield Strength in Mpa 165 min. Elongation in % 2.5 min. Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
384	AA	USA	Casting
AA315	AS	Australia	Ingot and Casting
A03840	UNS	USA	Ingot and Casting
A03840	SAE	USA	Ingot and Casting
384.0	NBR	Brazil	Casting
384.0	NMX	Maxico	Casting
B 85 SC114A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com