

## Material: ASTM B275 G8A

### Standard Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** ASTM B275 Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.250 max.	As-Cast	
Iron	Fe %	1.800 max.		
Magnesium	Mg %	7.500 - 8.500		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.150 max.		
Silicon	Si %	0.350 max.		
Tin	Sn %	0.150 max.		
Zinc	Zn %	0.150 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa   310 min. Yield Strength in Mpa   190 min. Elongation in %   5 min. Reduction of Area in %   - Hardness in HB   - Impact in Joule   -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
218	AA	USA	Casting
B85 G8A	ASTM	USA	Casting
B275 518.0	ASTM	USA	Casting
B85 518.0	ASTM	USA	Casting
A05180	UNS	USA	Casting
518.0	SAE	USA	Casting
ADC5	JIS	Japan	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)