

Material: ASTM B30 C83800

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B30 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.250 max.		
Ni + Co	Ni% + Co%	0.800 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	5.800 - 6.800		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	3.500 - 4.200		
Zinc	Zn %	5.500 - 8.000		
Copper	Cu %	82.000 - 83.500	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	205 min.
			Yield Strength in Mpa	90 - 95
			Elongation in %	16 - 20
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C83800	UNS	USA	Rod, Bar, Tube and Shapes
C83800	SAE	USA	Casting
B145-4B	ASTM	USA	Casting
B505 C83800	ASTM	USA	Casting
CA838	SAE	USA	Casting
B584 C83800	ASTM	USA	Casting
SB-505 C83800	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com