

Material: ASTM B30 C84200

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B30 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|-----------|-----------------|---|--|
| Aluminium | Al % | 0.005 max. | As-Cast | |
| Iron | Fe % | 0.350 max. | | |
| Ni + Co | Ni% + Co% | 0.800 max. | | |
| Phosphorus | P % | 0.020 max. | | |
| Lead | Pb % | 2.000 - 2.800 | | |
| Sulphur | S % | 0.080 max. | | |
| Antimony | Sb % | 0.250 max. | | |
| Silicon | Si % | 0.005 max. | | |
| Tin | Sn % | 4.300 - 6.000 | | |
| Zinc | Zn % | 10.000 - 16.000 | | |
| Copper | Cu % | 78.000 - 82.000 | Mechanical Properties Tensile Strength in Mpa 221 min. Yield Strength in Mpa 110 min. Elongation in % 13 min. Reduction of Area in % - Hardness in BHN - Impact in Joule - | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|---------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| C84200 | UNS | USA | Rod, Bar, Tube and Shapes |
| B505 C84200 | ASTM | USA | Casting |
| SB-505 C84200 | ASME | USA | Casting |
| C83800 | UNS | USA | Casting |
| - | - | - | - |
| - | - | - | - |
| - | - | - | - |

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com