

Material: ASTM B30 C86300

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B30 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	5.000 - 7.500	As-Cast	
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	2.500 - 5.000		
Ni + Co	Ni% + Co%	0.800 max.		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.100 max.		
Zinc	Zn %	22.000 - 28.000		
Copper	Cu %	60.000 - 66.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	758 min.
-	-	-	Yield Strength in Mpa	414 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C86300	UNS	USA	Rod, Bar, Tube and Shapes
B271 C86300	ASTM	USA	Casting
CA863	SAE	USA	Casting
SAE 430B	SAE	USA	Casting
SB-505 C86300	ASME	USA	Casting
SB-584 C86300	ASME	USA	Casting
C86300	AS	Australia	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com