

Material: ASTM B30 C93500

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B30 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.100 max.		
Ni + Co	Ni% + Co%	0.800 max.		
Phosphorus	P %	0.040 max.		
Lead	Pb %	8.500 - 9.700		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.300 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	4.500 - 5.500		
Zinc	Zn %	0.500 - 1.500		
Copper	Cu %	83.00 - 85.000	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	193 min.
			Yield Strength in Mpa	83 min.
			Elongation in %	15 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C93500	UNS	USA	Rod, Bar, Tube and Shapes
B271 C93500	ASTM	USA	Casting
SB-505 C93500	ASME	USA	Casting
SB-584 C93500	ASME	USA	Casting
C93500	SAE	USA	Casting
CA935	SAE	USA	Casting
C93500	AS	Australia	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com