

## Material: ASTM B30 C93900

### Standard Specification for Copper Alloys Ingot and Casting

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASTM B30 Copper Alloys Ingot and Casting

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.350 max.		
Ni + Co	Ni% + Co%	0.800 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	14.000 - 17.700		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.500 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	5.300 - 7.000		
Zinc	Zn %	1.500 max.		
Copper	Cu %	76.500 - 79.500	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	172 min.
-	-	-	Yield Strength in Mpa	110 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C93900	UNS	USA	Rod, Bar, Tube and Shapes
B505 C93900	ASTM	USA	Casting
SB-505 C93900	ASME	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)