

Material: ASTM B30 C95600

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B30 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	6.000 - 8.000	As-Cast	
Ni + Co	Ni% + Co%	0.250 max.		
Silicon	Si %	1.800 - 3.300		
Copper	Cu %	88.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	195 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C95600	UNS	USA	Rod, Bar, Tube and Shapes
B148 C95600	ASTM	USA	Casting
B148 Grade E	ASTM	USA	Casting
B30 9E	ASTM	USA	Ingot and Casting
SB-148 C95600	ASME	USA	Casting
SB-148 Grade 9E	ASME	USA	Casting
SB-148 Grade E	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com