

Material: ASTM B505 Leaded Nickel Bronze UNS C97600

Standard Specification for Copper Alloy Continuous Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B505 / 505M Copper Alloys for Continuous Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	3.500 - 4.500	As-Cast	
Lead	Pb %	3.000 - 5.000		
Zinc	Zn %	3.000 - 9.000		
Ni + Cu	Ni% + Cu%	19.000 - 21.500		
Iron	Fe %	1.500 max.		
Antimony	Sb %	0.250 max.		
Sulphur	S %	0.080 max.		
Phosphorus	P %	0.050 max.		
Aluminium	Al %	0.005 max.		
Manganese	Mn %	1.000 max.		
Silicon	Si %	0.150 max.	Mechanical Properties	
Copper	Cu %	63.000 - 67.000		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	276 min.
			Yield Strength in Mpa	138 min.
			Elongation in %	10 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 11A	ASTM	USA	Ingot and Casting
B30 C97600	ASTM	USA	Ingot and Casting
B271 C97600	ASTM	USA	Casting
B505 C97600	ASTM	USA	Casting
B584 C97600	ASTM	USA	Casting
SB-505 C97600	ASME	USA	Casting
SB-584 C97600	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com