

Material: ASTM B505 Leaded Nickel Bronze UNS C97800

Standard Specification for Copper Alloy Continuous Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B505 / 505M Copper Alloys for Continuous Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	4.000 - 5.500	As-Cast	
Lead	Pb %	1.000 - 2.500		
Zinc	Zn %	1.000 - 4.000		
Ni + Cu	Ni% + Cu%	24.000 - 27.000		
Iron	Fe %	1.500 max.		
Antimony	Sb %	0.200 max.		
Sulphur	S %	0.080 max.		
Phosphorus	P %	0.050 max.		
Aluminium	Al %	0.005 max.		
Manganese	Mn %	1.000 max.		
Silicon	Si %	0.150 max.	Mechanical Properties	
Copper	Cu %	64.000 - 67.000		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	310 min.
			Yield Strength in Mpa	152 min.
			Elongation in %	8 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B149-11B	ASTM	USA	Casting
B30 C97800	ASTM	USA	Ingot and Casting
B271 C97800	ASTM	USA	Casting
B505 C97800	ASTM	USA	Casting
B584 C97800	ASTM	USA	Casting
SB-505 C97800	ASME	USA	Casting
SB-584 C97800	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com