

# Material: ASTM B505 Leaded Semi-Red Brass UNS C84400

## Standard Specification for Copper Alloy Continuous Casting

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASTM B505 / 505M Copper Alloys for Continuous Casting

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	2.300 - 3.500	As-Cast	
Lead	Pb %	6.000 - 8.000		
Zinc	Zn %	7.000 - 10.000		
Ni + Cu	Ni% + Cu%	1.000 max.		
Iron	Fe %	0.400 max.		
Antimony	Sb %	0.250 max.		
Sulphur	S %	0.080 max.		
Phosphorus	P %	1.500 max.		
Aluminium	Al %	0.005 max.		
Silicon	Si %	0.005 max.		
Copper	Cu %	78.000 - 82.000		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	207 min.
			Yield Strength in Mpa	103 min.
			Elongation in %	16 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B145-5A	ASTM	USA	Casting
B271 C84400	ASTM	USA	Casting
B30 5A	ASTM	USA	Casting
B30 C84400	ASTM	USA	Casting
B505 C84400	ASTM	USA	Casting
SB-505 C84400	ASME	USA	Casting
SB-584 C84400	ASME	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)