

Material: ASTM B505 Tin Bronze UNS C91000

Standard Specification for Copper Alloy Continuous Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B505 / 505M Copper Alloys for Continuous Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	14.000 - 16.000	As-Cast	
Lead	Pb %	0.200 max.		
Zinc	Zn %	1.500 max.		
Ni + Cu	Ni% + Cu%	0.800 max.		
Iron	Fe %	0.100 max.		
Antimony	Sb %	0.200 max.		
Sulphur	S %	0.050 max.		
Phosphorus	P %	1.500 max.		
Aluminium	Al %	0.005 max.		
Silicon	Si %	0.005 max.		
Copper	Cu %	84.000 - 86.000		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	207 min.
			Yield Strength in Mpa	-
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in BHN	160 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C91000	ASTM	USA	Ingot and Casting
B505 C91000	ASTM	USA	Casting
SB-505 C91000	ASME	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com