

Material: ASTM B505 UNS C96400

Standard Specification for Copper Alloy Continuous Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B505 / 505M Copper Alloys for Continuous Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Lead	Pb %	0.010 max.	As-Cast	
Ni + Cu	Ni% + Cu%	28.000 - 32.000		
Iron	Fe %	0.250 - 1.500		
Sulphur	S %	0.020 max.		
Phosphorus	P %	0.020 max.		
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.500 max.		
Copper	Cu %	65.000 - 69.000		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	448 min.
			Yield Strength in Mpa	241 min.
			Elongation in %	25 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C96400	ASTM	USA	Ingot and Casting
B369 C96400	ASTM	USA	Casting
B505 C96400	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com