

Material: ASTM F468 Ni400HF

Standard Specification for Nickel-Copper Alloy, Corrosion Resistant Sheet, Strip and Plate

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM F467 Ni400 Nickel-Copper Alloy, Corrosion Resistant Sheet, Strip and Plate

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Sheet, Strip and Plate

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.		
Iron	Fe %	2.500 max.		
Sulphur	S %	0.024 max.		
Nickel	Ni %	63.000 - 70.000		
Copper	Cu %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 480 - 825 Yield Strength in Mpa 205 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HRC 60 - 95 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Monel 400	SAE	USA	Sheet, Strip and Plate
F467 Ni400	ASTM	USA	Sheet, Strip and Plate
SF467 Ni400	ASME	USA	Sheet, Strip and Plate
SF-468 Ni400	ASME	USA	Sheet, Strip and Plate
SF-468 Ni400HF	ASME	USA	Sheet, Strip and Plate
NCuR	JIS	Japan	Strip
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com