

# Material: ASTM F901 6061

## Standard Specification For Aluminium Alloy Transmission Tower Bolt and Nut

**Group:** Non-Ferrous Aluminium Alloys

**Sub Group:** ASTM F901 6061 Aluminium Alloy Transmission Tower Bolt and Nut

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bolt and Nut

Chemical Composition		
Silicon	Si %	0.400 - 0.800
Chromium	Cr %	0.040 - 0.350
Manganese	Mn %	0.150 max.
Magnesium	Mg %	0.800 - 1.200
Copper	Cu %	0.150 - 0.400
Iron	Fe %	0.700 max.
Zinc	Zn %	0.250 max.
Titanium	Ti %	0.150 max.
Other	Ot %	1.000 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Temper or Solution Treated or Aging

Mechanical Properties	
Tensile Strength in Mpa	121.2 - 328.5
Yield Strength in Mpa	49 - 305.1
Elongation in %	10 - 33.5
Reduction of Area in %	41.835 - 55.904
Hardness in HB	104 - 106
Impact in Joule	12.1 - 21.8 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
6061	SAE	USA	Bar, Rod, Shapes, Tube and Wire, Extrusion
6061	AS	Australia	Plate, Sheet, Rod, Bar, Wire and Strip
SB-210 6061	ASME	USA	Tube
Alclad 6061	SAE	USA	Plate and Sheet
A05050	UNS	USA	Casting
A 6061S	JIS	Japan	Bar, Rod, Shapes, Tube and Wire, Extrusion
AL-P6061	UNI	Italy	Tube

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India