

Material: BS 10213 EN 1.1118

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS 10213 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment															
Carbon	C %	0.200 - 0.250	Normalising or Annealing or Hardening + Tempering															
Silicon	Si %	0.600 max.																
Manganese	Mn %	1.500 - 1.800																
Phosphorus	P %	0.020 max.																
Sulphur	S %	0.015 max.																
Chromium	Cr %	0.300 max.																
Nickel	Ni %	0.400 max.																
Molybdenum	Mo %	0.150 max.																
Copper	Cu %	0.300 max.																
Vanadium	V %	0.050 max.																
Iron	Fe %	Balance	<table border="1"> <thead> <tr> <th colspan="2">Mechanical Properties</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength in Mpa</td> <td>650 - 800</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>500 min.</td> </tr> <tr> <td>Elongation in %</td> <td>15 min.</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in BHN</td> <td>-</td> </tr> <tr> <td>Impact in Joule</td> <td>27 min. @ -30°C</td> </tr> </tbody> </table>		Mechanical Properties		Tensile Strength in Mpa	650 - 800	Yield Strength in Mpa	500 min.	Elongation in %	15 min.	Reduction of Area in %	-	Hardness in BHN	-	Impact in Joule	27 min. @ -30°C
Mechanical Properties																		
Tensile Strength in Mpa	650 - 800																	
Yield Strength in Mpa	500 min.																	
Elongation in %	15 min.																	
Reduction of Area in %	-																	
Hardness in BHN	-																	
Impact in Joule	27 min. @ -30°C																	
-	-	-																
-	-	-																
-	-	-																
-	-	-																
-	-	-																

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.1118	EN	Germany	Casting
1.1119	EN	European Union	Casting
1.1119	BS	British	Casting
GS-24Mn6	DIN	Germany	Casting
GS-23Mn6	DIN	Germany	Casting
G23 Mn6	EN	European Union	Casting
GS-24Mn6	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com