

Material: BS 10213 EN 1.5419

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS 10213 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment															
Carbon	C %	0.150 - 0.230	Normalising or Annealing or Hardening + Tempering															
Silicon	Si %	0.600 max.																
Manganese	Mn %	0.500 - 1.000																
Phosphorus	P %	0.025 max.																
Sulphur	S %	0.020 max.																
Chromium	Cr %	0.300 max.																
Nickel	Ni %	0.400 max.																
Molybdenum	Mo %	0.400 - 0.600																
Copper	Cu %	0.300 max.																
Vanadium	V %	0.050 max.																
Iron	Fe %	Balance	<table border="1"> <thead> <tr> <th colspan="2">Mechanical Properties</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength in Mpa</td> <td>440 - 590</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>245 min.</td> </tr> <tr> <td>Elongation in %</td> <td>22 min.</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in BHN</td> <td>-</td> </tr> <tr> <td>Impact in Joule</td> <td>27 min. @ RT</td> </tr> </tbody> </table>		Mechanical Properties		Tensile Strength in Mpa	440 - 590	Yield Strength in Mpa	245 min.	Elongation in %	22 min.	Reduction of Area in %	-	Hardness in BHN	-	Impact in Joule	27 min. @ RT
Mechanical Properties																		
Tensile Strength in Mpa	440 - 590																	
Yield Strength in Mpa	245 min.																	
Elongation in %	22 min.																	
Reduction of Area in %	-																	
Hardness in BHN	-																	
Impact in Joule	27 min. @ RT																	
-	-	-																
-	-	-																
-	-	-																
-	-	-																
-	-	-																

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G18Mo5	UNI	Italy	Steel
StE285	DIN	Germany	Steel
TS 15 CD 2-05	AFNOR NF	France	Steel
WStE 285	DIN	Germany	Steel
1.0486	BS	British	Steel
1.0488	BS	British	Steel
1.0487	BS	British	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com