

Material: BS 10213 EN 1.7379

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS 10213 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 - 0.200	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.900		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	2.000 - 2.500		
Nickel	Ni %	0.400 max.		
Molybdenum	Mo %	0.900 - 1.200		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 590 - 740 Yield Strength in Mpa 400 min. Elongation in % 18 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 40 min. @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J21890	UNS	USA	Casting
SA-217 Grade WC	ASME	USA	Casting
10 CrMo 9-10	AFNOR NF	France	Steel
622	BS	British	Bar
10 CrMo 9-10	DIN	Germany	Forging
10 CrMo 9-10	EN	European Union	Casting
10 CrMo 9-10	UNI	Italy	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com