

Material: BS 10213 EN GX8CrNi12

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 10213 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	11.500 - 12.500		
Nickel	Ni %	0.800 - 1.500		
Molybdenum	Mo %	0.500 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.080 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 540 - 690 Yield Strength in Mpa 355 min. Elongation in % 18 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 45 min. @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4107	EN	European Union	Casting
1.4107	BS	British	Casting
1.4107	DIN	Germany	Casting
GX8CrNi12	UNI	Italy	Casting
GX8CrNi12	ONORM	Australia	Casting
GX8CrNi12	DIN	Germany	Casting
GX8CrNi12	AFNOR NF	France	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com