

Material: BS 3100 Grade 310C45

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 3100 Grade 310C45 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.500 max.
Silicon	Si %	3.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.050 max.
Sulphur	S %	0.050 max.
Chromium	Cr %	22.000 - 27.000
Molybdenum	Mo %	1.500 max.
Nickel	Ni %	17.000 - 22.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	400 min.
Yield Strength in Mpa	200 min.
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in BHN	180 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Z 40CN25.20-M	AFNOR NF	France	Casting
1.4848	CSN	Czech Republic	Casting
1.4848	DIN	Germany	Casting
1.4848	MSZ	Hungary	Casting
1.4848	AFNOR NF	France	Casting
1.4848	UNI	Italy	Casting
1.4848	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India