

Material: BS 3100 Grade 316C16LT196

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 3100 Grade 316C16LT196 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	17.000 - 21.000		
Molybdenum	Mo %	2.000 - 3.000		
Nickel	Ni %	9.000 min.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	480 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	26 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	41 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
316C16	BS	British	Casting
Z 6 CND 18.12 M	AFNOR NF	France	Casting
317C16	BS	British	Casting
318C17	BS	British	Casting
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com